

Technical Data Sheet

Iron powder

Revision Date:4/2/2026

1 IDENTIFICATION OF THE SUBSTANCE/PREPARATION AND THE COMPANY / UNDERTAKING

Product name	Iron powder
Product code	NM-0029-UP
CAS	7439-89-6
Supplier	IoLiTec Ionic Liquids Technologies GmbH Im Zukunftspark 9 D-74076 Heilbronn Germany
Telephone	+49 (0)7131 - 898390
Fax	+49 (0)7131 - 89839109
Emergency telephone	+49 (0)151-41255671

2 COMPOSITION / INFORMATION ON INGREDIENTS

Ingredient name	Iron powder
CAS No.	7439-89-6
Empirical Formula	Fe
Molecular weight	55.85 g/mol
Purity	99.9%
O content	~ 5.0%
Morphology	spherical
Average Particle Size	60-80 nm (TEM)
Specific Surface Area	7 m ² /g (BET)
Relative Density	7.87 g/cm ³
Bulk Density	0.5 g/cm ³
Melting point	1535°C

Technical Data Sheet


Iron powder

Revision Date:4/2/2026

3 CONTENT OF IMPURITIES

Impurity	Content
Cu	400 ppm
Ni	300 ppm
Al	200 ppm
Ca	50 ppm
Cr	50 ppm
Mo	50 ppm
Ti	50 ppm
Si	30 ppm
Sn	30 ppm
Pb	20 ppm
Mg	10 ppm
Mn	10 ppm

4 TEM IMAGE



Technical Data Sheet

Iron powder

Revision Date:4/2/2026

5 OTHER INFORMATION

DISCLAIMER

THE ABOVE INFORMATION IS BELIEVED TO BE CORRECT BUT DOES NOT PURPOPOSED TO BE ALL INCLUSIVE AND SHALL BE USED ONLY AS A GUIDE. IOLITEC SHALL NOT BE HELD LIABLE FOR ANY DAMAGE RESULTING FROM HANDLING OR FROM CONTACT WITH THE ABOVE PRODUCT. THIS INFORMATION RELATES ONLY TO THE SPECIFIC MATERIAL DESIGNATED AND MAY NOT BE VALID FOR SUCH MATERIAL USED IN COMBINATION WITH ANY OTHER MATERIALS OR ANY PROCESS. IT IS THE USERE'S RESPONISIBILTY TO SATISFY HIMSELF AS TO THE SUITABILITY OF SUCH INFORMATION FOR HIS OWN PARTICULAR USE.

IN NO WAY SHALL IOLITEC BE LIABLE FOR ANY CLAIMS, LOSSES OR DAMAGES OF ANY THIRD PARTY OR FOR THE LOST PROFITS OR ANY SPECIAL, INDIRECT, INCIDENTAL, CONSEQUENTIAL OR EXEMPLARY DAMAGES, HOWSOEVER ARISING, EVEN IF THE COMPANY HAS BEEN ADVISED OF THE POSSIBILITY OF SUCH DAMAGES.